



Technical Data

VB-250 (11 mil) Vapor Retarder

DIVISION: 07260, 03300

1.0 PRODUCT NAME

VB-250 (11 mil)
Class A Vapor Retarder
 Exceeds ASTM E 1745 class A, B & C
 Retarder Specifications

2.0 MANUFACTURER

Inteplast Group
 9 Peach Tree Hill Road
 Livingston, NJ 07039

Technical Assistance
 Tel: (877) 535-0555
 Fax: (800) 709-6002

3.0 PRODUCT DESCRIPTION

Uses: **VB-250 (11 mil) Vapor Retarder** is a high performance under slab vapor retarder developed for the construction industry to retard moisture migration through concrete slabs. It may also be used to control radon, methane, sulphates and many other soil contaminants.

3.1 COMPOSITION

VB-250 (11 mil) Vapor Retarder is manufactured to the highest standards with proprietary polyolefin resins. The manufacturing process for the **VB-250 (11 mil) Vapor Retarder** is made by IntePlus® XF Film, a three layer, co-extruded, cross-laminated system.

VB-250 (11 mil) vapor retarder is manufactured in 12.75 ft x 200 ft rolls (2550 ft²).

VB-250 (11 mil) vapor retarder weighs approximately 131 lbs. per roll.

4.0 TECHNICAL DATA

Applicable Standards:

ASTM, American Society for Testing & Materials

- ASTM E 1745 Standard Specification for Water Vapor Retarders used in Contact with Soil or Granular Fill Under Concrete Slabs.
- ASTM E 154 Standard Test Methods for Water Vapor Retarders used in Contact with Earth Under Concrete Slabs, on Walls, or as a Ground cover.
- ASTM D 1709 Standard Test Methods for Impact Resistance of Plastic Films by the Free Falling Dart Method.
- ASTM E 96 Standard Test Method for Water Vapor Transmission of Materials.
- ASTM D 882 Standard Test Method for Tensile Properties of Thin Plastic Sheeting.
- ASTM E 1643 Standard Practice for installation of Water Vapor Retarders used in Contact with Earth or Granular Fill Under Concrete Slabs.

ACI, American Concrete Institute

- ACI 302.1 R-04 Minimum Thickness (10 mil)

Table 1: Physical Properties of **VB-250 (11 mil) Vapor Retarder**

Classification	ASTM E 1745	Exceed Class A, B and C
Water Vapor Permeance	ASTM E 96	0.020 perms (US)
Tensile Strength	ASTM E 154-93 (ASTM D 882)	50 lbf/in
Puncture Resistance	ASTM D 1709	2400 grams
Life Expectancy	ASTM E 154	indefinite
Chemical Resistance	ASTM E 154	unaffected



Technical Data

VB-250 (11 mil) Vapor Retarder

DIVISION: 07260, 03300

5.0 INSTALLATION

VB-250 (11 mil) Vapor Retarder shall be installed over tamped earth, sand or aggregate base by unrolling and completely covering area to receive building slab or specified area. Overlap all seams a minimum of 6" and seal with **Barrier-Bac Seam Tape** or heat weld. All penetrations must be sealed with **Barrier-Bac** membrane and **Barrier-Bac Seam Tape** per manufacturer's recommendations.

Specific project details and recommendations can be provided by *Inteplast Group* upon request.

6.0 AVAILABILITY & COST

VB-250 (11 mil) Vapor Retarder is available nationally through our network of building supply companies. Please contact our corporate office for a distributor in your area. **VB-250 (11 mil) Vapor Retarder** is cost efficient. Pricing can be obtained by contacting your local **Barrier-Bac** distributors or sales representatives.

7.0 WARRANTY

We warrant and guarantee our specifications as published. Published test results are based upon accepted industry practice as well as the test methods called for and listed on our test documents. We believe, to

the best of our knowledge, that our published results are accurate and reliable and that they represent our vapor retarder membrane. *Inteplast Group* cannot control site conditions and improper installation practices. Therefore, no warranty, expressed or implied, is given, including those of merchantability, fitness for a particular purpose or any other matter with respect to the product.

8.0 MAINTENANCE

No maintenance is required.

9.0 TECHNICAL SERVICES

Technical services for all of our products can be obtained by calling our corporate office.

Corporate Office:
(877)535-0555

10.0 FILING SYSTEMS

Barrier-Bac brochures are available from **Barrier-Bac** distributors, sales representatives, *Inteplast Group* and on our website:
<http://www.BarrierBac.com>



INTEPLAST GROUP

OFFICE: 9 Peach Tree Hill Rd., Livingston, NJ 07039
PLANT: 101 Inteplast Blvd., Lolita, TX 77971

TEL: 877-535-0555
FAX: 800-709-6002

E-MAIL: info@BarrierBac.com

WEB SITE: www.BarrierBac.com / www.inteplast.com