



Version: January 1, 2024

Guide Specification

VB-250 (10mil) Vapor Retarder

UNDER-SLAB VAPOR RETARDER (033000&072600)

PART I - GENERAL

1.1 SUMMARY

- A. Products Supplied Under This Section
 - 1. Vapor Retarder, Seam Tape & Accessories for installation under concrete slabs
- **B.** Related Sections
 - 1. Section 033000 Cast-in-place Concrete
 - 2. Section 072600 Vapor Retarder

1.2 REFERENCES

A. American Society for Testing and Materials (ASTM)

- 1. ASTM E 1745-17 Standard Specification for Plastic Water Vapor Retarders used in Con- tact with Soil or Granular Fill under Concrete Slabs.
- 2. ASTM E 154 / E 154M-08 Standard Test Methods for Water Vapor Retarders used in Contact with Earth under Concrete Slabs, on Walls, or as Ground Cover.
- 3. ASTM E 96-16 Standard Test Methods for Water Vapor Transmission of Materials.
- 4. ASTM E 1643-18 Selection, Design, Installation, and Inspection of Water Vapor Retarders used in Contact with Earth or Granular Fill under Concrete Slabs.
- 5. ASTM D 882 Standard Test Method for Tensile Properties of Thin Plastic.
- 6. ASTM D 1709 Standard Test Method for Impact Resistance of Plastic.
- 7. ISO / TS 11665-13 Method to test Radon Diffusion Coefficient in Radon-Proof Membrane.
- 8. ASTM D 1434 Standard Test Method for Determining Gas Permeability.

B. American Concrete Institute (ACI)

1. ACI 302.2R-06 Guide for Concrete Slabs that Receive Moisture-Sensitive Flooring Materials. Vapor Retarder component is not less than 10 mils thick.

1.3 SUBMITTALS

A. Quality Control / Assurance

- 1. Summary of test results as per paragraph 7 of ASTM E 1745.
- 2. Manufacturer's samples, literature.
- 3. Manufacturer's installation instructions for placement, seaming and penetration repair

PART II - PRODUCTS

2.1 MATERIALS

A. Vapor Retarder

- 1. Manufactured with proprietary polyolefin resins
 - a. Minimum 10 mil thick plastic geo-membrane

b. Water Vapor Retarder ASTM E 1745 meet or exceed Class A (Plastics)

c. Water Vapor Permeance ASTM E 96 0.0204 Perms (US)

d. Puncture Resistance ASTM D1709 Class A minimum 2480 grams



Guide Specification

VB-250 (10mil) Vapor Retarder

UNDER-SLAB VAPOR RETARDER (033000&072600)

e. Tensile Strength ASTM D 882 Class A minimum 54.2 lbf/in

f. Radon Diffusion Coefficient ISO / TS 11665-13 7.0×10^{-12} m²/S

g. Methane Permeance ASTM D 1434 288.6 cm³(m².Atm.Day)

B. Approved Manufacturers

1. Barrier-Bac VB250 manufactured by Inteplast Group, 877-535-0555, www.BarrierBac.com

- 2. Vapor Block 10 manufactured by Raven Industries, 605-336-2750, www.ravenind.com
- 3. Griffolyn 10 mil manufactured by Reef Industries, 800-231-6074, www.reefindustries.com

2.2 ACCESSORIES

A. Seam Options

1. Tape manufactured and/or supplied by the approved manufacturers listed in section 2.1 Materials (B.)

a. Water Vapor Permeance ASTM E 96B 0.1 Perms(maximum)

B. Pipe Boots

1. Construct Pipe Boots from Vapor Retarder material and pressure sensitive tape per manufacturer's instructions.

C Mastic

- 1. Mastic must have the following qualities:
 - a. Water Vapor Transmission ASTM E 96 0.1 perms or lower

PART III - EXECUTION

3.1 PREPARATION

- A. Ensure that base material is approved by Architect or Geotechnical Engineer
 - 1. Level and compact base material

3.2 INSTALLATION

- A. Install vapor retarder in accordance with manufacturer's instructions and ASTM E 1643:
 - 1. Unroll vapor retarder with the longest dimension parallel with the direction of the concrete placement.
 - 2. Lap vapor retarder over footings and/or seal to foundation walls.
 - 3. Overlap joints 6 inches and seal with manufacturer's tape.
 - 4. Seal all penetrations (including pipes) per manufacturer's instructions.
 - 5. No penetration of the vapor retarder is allowed except for reinforcing steel and permanent utilities.
 - 7. Repair damaged areas by cutting patches of vapor retarder, overlapping damaged area 6 inches and taping all sides with tape.